


SWATCHBOOK: ROSCOLUX
COLOR FILTER: #374 SEA GREEN
DESCRIPTION: Color Effects Lighting Filter.
TRANSMISSION = 26% or -2.0 stop loss
MIREL SHIFT = Not Applicable.
CC EQUIVALENT = Not Applicable.

COLORIMETRIC DATA

OBSERVER: CIE 1964 10°
SOURCE:

- 'A' (tungsten)
- 'D65' (daylight)




| HUNTER LAB SOURCE A | |
|---------------------|---------|
| L* | 57.347 |
| A* | -69.660 |
| B* | -32.178 |

| HUNTER LAB SOURCE D65 | |
|-----------------------|----------|
| L* | 64.2433 |
| A* | -49.637 |
| B* | -18.2437 |

| CIE 1964 SOURCE A | |
|-------------------|--------|
| Y | 26.280 |
| (x) | 0.259 |
| (y) | 0.437 |

| CIE 1964 SOURCE D65 | |
|---------------------|--------|
| Y | 33.102 |
| (x) | 0.189 |
| (y) | 0.317 |



| | | | | | | | | | | | | | | | | | | | | |
|---------|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|
| nm. | 360 | 380 | 400 | 420 | 440 | 460 | 480 | 500 | 520 | 540 | 560 | 580 | 600 | 620 | 640 | 660 | 680 | 700 | 720 | 740 |
| trans % | 14 | 21 | 26 | 30 | 41 | 54 | 63 | 63 | 56 | 42 | 27 | 14 | 7 | 4 | 3 | 2 | 1 | 5 | 22 | 49 |

MATERIAL SPECIFICATIONS:

General Description: Co-extruded Polycarbonate Film
Substrate: PC (Polycarbonate)
Thickness: 3.0 mil (.003" or 76.2 micron)

Manufactured in: U.S.A.

AVAILABLE SIZES:

- ✓ 20 in. x 24 in. sheets (50cm x 60cm)
- ✓ 24 in. x 25 ft. rolls (60cm x 7.62m)
- 0 48 in. x 25 ft. rolls (121cm x 7.62m)
- 0 60 in. x 20 ft. rolls (152.4cm x 6.10m)
- 0 13.5 in. Diameter Glass (34.3cm) - Cut to order